

Tundra® Tundra® SS

Tubular Foam Insulation



Tundra® and Tundra SS premium quality closed-cell polyethylene foam insulations are used in residential, commercial and industrial projects to prevent heat loss and protect pipes from freezing. Tundra SS has an integrated self-sealing system that makes it quick and easy to install.

APPLICATIONS

Tundra is used to retard heat loss on hot water pipes and prevent freezing of all water pipes. It is available in wall thicknesses of 3/8", 1/2", 3/4" and 1", in sizes ranging from 3/8" CTS to 4" IPS.

Tundra has a low thermal conductivity and very low water vapor transmission rate. This low density product demonstrates excellent thermal, physical and chemical resistant properties and has a broad service temperature range between -297°F and 200°F (-183°C and 93°C). It can be installed in commercial, industrial and residential insulation projects. It is acceptable for use with heat tracing/heat tape.

BENEFITS

Tundra and Tundra SS are fiber-free and 100% non-particulating polyethylene foam pipe insulation. Its closed-cell structure won't wick moisture and helps prevent the absorption of condensation that could cause mold to develop over time. Tundra SS has an easy-to-install self-seal closure system.

INSTALLATION

Tundra pipe insulation is semi-slit, and can be completely slit by hand.

Tundra SS is pre-slit with a factory applied pressure sensitive adhesive (PSA) to both seam surfaces and has a release liner for easy installation. All butt joints should be properly sealed. Tundra and Tundra SS are easy to cut with a knife and can be fabricated to go around P-traps and fittings.

Features

- CFC/HCFC Free
- Non-porous
- Low VOCs
- Halogen Free
- Fiber Free
- Resistant to Mold Growth
- Made in Canada

Specification Compliance

- ASTM C-1427, Type 1
- ASTM E 84/CAN ULC-S102.2 1" 25/50
- NFPA 90 A/B / Acceptable for use in duct/plenum applications

Technical Data: Tundra® and Tundra® SS

Approvals, Certifications, Compliances:

- Manufactured without CFCs, HFCs, HCFCs, PBDEs, or Formaldehyde
- Plenum Rated

Typical Properties

| Physical Properties | Testing Parameters | Tundra Insulation | Test Methods |
|--|--|---|--------------------------|
| Thermal Conductivity (K) Btu • in/hr • ft² • °F (W/mK) | 90°F (32°C) Mean Temperature 75°F (24°C) Mean Temperature 50°F (10°C) Mean Temperature | 0.275 (0.040) 0.270 (0.039) 0.265 (0.038) | ASTM C 177/C 518 |
| Operating Temperature Range Flexible to -100°F (-73°C) | Upper range Lower Range | 200°F (93°C) -297°F (-183°C) | |
| Water Vapor Permeability Dry Cup. Perm-In | | 0.02 | ASTM E 96 Procedure A |
| Ozone Resistance | | Pass | ASTM D 1171 |
| Chemical / Solvent Resistance | | Good | |
| Mildew Resistance / Air Erosion | | Pass | UL 181 |
| Flame Spread and Smoke Developed Index through 1" (25 mm) thickness* | | 25/50 rated | ASTM E 84/CAN ULC-S102.2 |

* Cellular plastics and thermoplastics, such as polyethylene/polyolefin insulation, that may drip, melt, delaminate or draw away from the fire, present unique problems and require careful interpretation of the test results.

R-Values

| Pipe O.D. or Nominal | | R Value | R Value | R Value | R Value |
|----------------------|--------|-------------------|-------------------|-------------------|-----------------|
| Insulation I.D. | | 3/8" (10 mm) Wall | 1/2" (13 mm) Wall | 3/4" (19 mm) Wall | 1" (25 mm) Wall |
| 3/8" | 10 mm | 2.8 | 3.7 | 6.1 | 8.6 |
| 1/2" | 13 mm | 2.5 | 3.4 | 5.6 | 7.9 |
| 5/8" | 16 mm | 2.5 | 3.3 | 5.3 | 7.4 |
| 3/4" | 19 mm | 2.3 | 3.2 | 5.1 | 7.1 |
| 7/8" | 22 mm | 2.3 | 3.1 | 4.8 | 6.8 |
| 1-1/8" | 29 mm | 2.2 | 3.0 | 4.5 | 6.3 |
| 1-3/8" | 35 mm | 2.0 | 2.8 | 4.3 | 6.0 |
| 1-5/8" | 41 mm | 2.1 | 2.7 | 4.3 | 5.9 |
| 2" | 50 mm | 1.8 | 2.5 | 3.9 | 5.4 |
| 2-1/8" | 54 mm | 2.1 | 2.7 | 4.1 | 5.6 |
| 2-3/8" | 62 mm | 1.8 | 2.4 | 3.8 | 5.2 |
| 2-5/8" | 67 mm | 2.1 | 2.6 | 4.0 | 5.4 |
| 2-7/8" | 72 mm | 1.8 | 2.4 | 3.7 | 5.0 |
| 3-1/8" | 79 mm | 2.1 | 2.6 | 3.9 | 5.3 |
| 3-1/2" | 89 mm | 1.8 | 2.3 | 3.6 | 4.9 |
| 3-5/8" | 92 mm | 2.5 | 2.6 | 3.9 | 5.2 |
| 4-1/8" | 105 mm | 2.5 | 2.7 | 3.9 | 5.2 |
| 4-1/2" | 115 mm | 1.7 | 2.3 | 3.5 | 4.7 |

Note: "R" values were calculated using a K factor of 0.27 (75° F, 24° C mean temp.) and nominal all thickness in each case. Lower operating temperatures will result in improved R values. Contact Technical Services for specific recommendations.

Outdoor Use

Painting with WB Finish or other protective jacketing is required to prevent damage to the insulation in exterior applications and to comply with the insulation protection sections of the International Energy Conservation Code (IECC) and ASHRAE 90.1.

ARMACELL LLC

TEL: 800.866.5638

info.us@armacell.com

www.armacell.us

153 Van Kirk Drive, Brampton, Ontario, Canada L7A 1A4



Armacell provides this information as a technical service. To the extent the information is derived from sources other than Armacell, Armacell is substantially, if not wholly, relying upon the other source(s) to provide accurate information. Information provided as a result of Armacell's own technical analysis and testing is accurate to the extent of our knowledge and ability, as of date of printing, using effective standardized methods and procedures. Each user of these products, or information, should perform their own tests to determine the safety, fitness and suitability of the products, or combination of products, for any foreseeable purposes, applications and uses by the user and by any third party to which the user may convey the products. Since Armacell cannot control the end use of this product, Armacell does not guarantee that the user will obtain the same results as published in this document. The data and information are provided as a technical service and are subject to change without notice.