

K-FONIK AB
OPEN CELL NBR/PVC



K-TEK ▶ K-FONIK AB		
▼ Specification ▼	▼ Classification ▼	▼ Notes ▼
UL 94	HF-1	Pass at 4.2mm (Listing in Progress)
UL 50 & 50E	--	Suitable for enclosure types 2, 3, 3R, 3S, 4, 4X, 5, 6, 6P, 12, 12K, and 13, including oil immersion (File #: JMST2.MH60641)

The K-FLEX® USA website contains the most recent version of all K-FLEX® USA literature. Please refer to the website for current versions of K-FLEX® USA literature at www.kflexusa.com

K-TEK K-FONIK AB ▶ TECHNICAL DATA		
Property ▼	Value ▼	Test method ▼
Polymer	NBR/PVC	
Cell structure	Open (Re-Bonded)	
Color	Primarily black	
Density	15 LB/FT ³	ASTM D1056
25% Compression Resistance	6.5-7.5 PSI Max	ASTM D1056
50% Compression Set	8% Max	ASTM D1056
Tensile	10 PSI Min	ASTM D412 (DIE A)
Elongation	25% Min	ASTM D412 (DIE A)
Flammability	Pass (Listing in Progress) Pass	UL 94 HF-1 FMVSS-302
Service temperature	-40°F to +185°F	
Thermal conductivity (75°F)	0.30 BTU-IN/HR-FT ² -°F	ASTM C177
Sound absorption	0.70 (1") NRC	ASTM C423
Sound blocking	14 RW (dB)	UNI EN ISO 717-1 :2007
Air erosion	4,000 FPM Rating	ASTM C1071

K-TEK K-FONIK AB ▶ RANGE								
Size ▼	THICKNESS				WIDTH		LENGTH	
	Min (mm) ▼	Max (mm) ▼	Min (in) ▼	Max (in) ▼	Min (in) ▼	Max (in) ▼	Min (ft) ▼	Max (ft) ▼
1/2" **	12.7	15.3	0.500	0.602	59.0	60.0	79.0	80.0
1"	25.4	30.1	1.000	1.185	59.0	60.0	79.0	80.0
2"	50.8	55.9	2.000	2.201	59.0	60.0	79.0	80.0

Full buns are over 19" thick.
* Sheet Thickness should be checked using a calibrated caliper.

© K-FLEX® US_LEA_K-FONIK_AB_V1_0920; K-FLEX® reserves the right to change data and technical requirements without notice.